



Product Information 产品信息

Paryls® Polyphenylsulfone(PPSU) K1565

Latest Revision: Feb. 24th, 2021

物理形态和储存 Physical form and storage

Paryls® PPSU K1565 颗粒以 25kg 内衬铝箔袋包装，可以无限期的保存在无破损的纸箱包装袋中。

Paryls® PPSU K1565 pellets are supplied in aluminum foil bags, which can be stored indefinitely, provided the packaging remains undamaged.

Paryls® PPSU K1565 吸水很快，因此材料在加工前至少需在 180℃ 真空烘箱或除湿式干燥机中干燥 6 小时。

Paryls® PPSU K1565 pellets absorb moisture very rapidly. Therefore, the pellets need to be dried at least 6h at 180 °C in a vacuum or dry air drier prior to processing.

产品特点 Products Features

Paryls® K1565 树脂是一种高流动性聚亚苯基砜（PPSU）。

Paruls® K1565, resin is a High liquidity Polyphenylsulfone (PPSU).

- 本色：PPSU K1565NC, 灰色：PPSU K1565GY, 黑色：PPSU K1565BK, 白色：PPSU K1565WH

注 Note

本资料内容基于我司目前掌握的知识和经验。由于存在诸多因素可能影响我们产品的应用和加工，因此本公司不排除用户进行试验研究的必要。本资料也不保证具体应用的适应性或某些性能的可靠性。这里的任何描述、图纸、照片、数据、大小、重量等可能不事先通知而更改，但不包括已经达成一致的合同。

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product.



未着色产品的典型值，在 23℃下 Typical values for uncolored product at 23°C	测试方法 Test method	单位 Unit	典型值 Typical Values
机械性能 Mechanical Properties			
拉伸强度 Tensile Strength	ISO 527-1/-2	MPa	70
拉伸模量 Tensile Modulus	ISO 527-1/-2	MPa	2270
屈服伸长率 Tensile Elongation(Yield)	ISO 527-1/-2	%	7.8
弯曲强度 Flexural Strength	ISO 178	MPa	105
弯曲模量 Flexural Modulus	ISO 178	MPa	2400
Izod 缺口冲击强度 Notched Izod Impact	ISO 180/A	KJ/m ²	68
热性能 Thermal Properties			
热变形温度 HDT/A @1.8MPa Heat Deflection Temperature	ISO 75-1/-2	°C	196
玻璃化转变温度，DSC，10°C/min Glass Transition Temperature	ISO 11357-1/-2	°C	220
线性膨胀系数@23°C，CLTE-Flow	ISO11359-1/-2	E-6/K	55
阻燃性 Flammability			
厚度 1.5mm Flame Rating@1.5mm thickness	UL94	Class	V-0
电性能 Electrical Properties			
体积电阻率 100V Volume Resistivity	IEC 60093	Ω · m	>1E13
表面电阻率 100V Surface Resistivity		Ω	>1E15
相对介电常数 Dielectric Constant	@100HZ	-	3.8
	@1MHZ	-	3.7
介电损耗因子 Dissipation factor	@100HZ	E-4	15
	@1MHZ	E-4	86
介电强度 K20/K20, (60*60*1 mm ³)Dielectric Strength	IEC 60243-1	KV/mm	44
相对漏电起痕指数，CTI	IEC 60112	-	150
一般及加工性能 General Properties and Processability			
密度 Density	ISO1183	g/cm ³	1.29
饱和吸水率@23°C/50%相对湿度 Moisture Absorption, Equilibrium 23°C/50% r.h	ISO62	%	0.6
模塑收缩率（平行）Mold shrinkage(Flow)	ISO 2577, 294-4	-	0.9
模塑收缩率（垂直）Mold shrinkage (Vertical)	ISO 2577, 294-4	-	1.0
熔融指数 MFR @365°C/5kg	ISO 1133	g/10min	60-80
熔体温度范围，注塑/挤出成型 Processing (Melt)Temp, Injection/Extrusion	-	°C	350-390
模具温度范围，注塑/挤出成型 Mold Temp, Injection/Extrusion	-	°C	140-180

备注 Notes:

典型值 Typical values: 此典型值不应被解释为技术规范 These are not to be construed as specifications.